

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A method for protecting a substrate comprising (a) providing a substrate having at least one surface, (b) applying to at least part of said surface an overlay thermosettable resin, (c) applying to at least part of said surface a ~~substituted~~ polysiloxane substituted with organic groups having from one to seven carbon atoms such that the polysiloxane has an average of 0.3 to 1.5 carbon atoms per silicon atom, wherein at least a portion of said overlay thermosettable resin and at least a portion of said polysiloxane are applied to the same part of said surface and then (d) at least partially curing said overlay thermosettable resin.
2. (original) The method of claim 1 wherein said overlay thermosettable resin and said polysiloxane are applied to said surface simultaneously.
3. (original) The method of claim 1 wherein said overlay thermosettable resin and said polysiloxane are applied to said surface separately.
4. (cancelled)
5. (previously presented) The method of claim 1 wherein said polysiloxane comprises (a) a polysilsesquioxane having repeating units of the formula
$$(\text{RSiO}_{3/2})$$
wherein R is a single group or mixture of substituted or unsubstituted alkyl or aryl groups having from one to seven carbon atoms; or
(b) condensates of hydrolysates of the formula $\text{R}_x\text{Si}(\text{OR}')_y$ wherein $x + y$ is 4 and x is from 0 to 2 and y is from 2 to 4; R is a single alkyl or aryl group or mixture of alkyl or aryl groups

comprising up to 7 carbon atoms, optionally substituted with halogen atoms, mercapto groups, and/or epoxy groups; and R' is an alkyl radical with 1 to 4 carbon atoms.

6. (previously presented) The method of claim 1 wherein said overlay thermoset resin comprises at least one resin selected from the group consisting of phenolics, epoxies, polyesters, polyurethanes, and aminoplasts.

7. (original) The method of claim 1 wherein said substrate comprises a decorative inner layer having at least one decorative surface and said overlay thermosettable resin and said polysiloxane are applied to at least a portion of said decorative surface.

8. (original) The method of claim 7 wherein said decorative inner layer comprises a thermosettable resin that is compatible with said overlay thermosettable resin.

9. (currently amended) A protective overlay comprising an at least partially cured overlay thermosettable resin and a substituted polysiloxane substituted with organic groups having from one to eight carbon atoms such that the polysiloxane has an average of 0.3 to 1.5 carbon atoms per silicon atom.

10. (cancelled)

11. (previously presented) The overlay claim 9 wherein said polysiloxane comprises (a) a polysilsesquioxane having repeating units of the formula



wherein R is a single group or mixture of substituted or unsubstituted alkyl or aryl groups having from one to seven carbon atoms; or

(b) condensates of hydrosilyates of the formula $\text{R}_x\text{Si}(\text{OR}')_y$ wherein $x + y$ is 4 and x is from 0 to 2 and y is from 2 to 4; R is a single alkyl or aryl group or mixture of alkyl or aryl groups comprising up to 7 carbon atoms, optionally substituted with halogen atoms, mercapto groups, and/or epoxy groups; and R' is an alkyl radical with 1 to 4 carbon atoms.

12. (previously presented) The overlay of claim 9 wherein said overlay thermoset resin comprises at least one resin selected from the group consisting of phenolics, epoxies, polyesters, polyurethanes, and aminoplasts.

13. (currently amended) A decorative laminate comprising (a) a decorative inner layer having at least one decorative surface and (b) an overlay layer disposed on at least a portion of said decorative surface wherein said overlay comprises an at least partially cured overlay thermosettable resin and a substituted polysiloxane substituted with organic groups having from one to eight carbon atoms such that the polysiloxane has an average of 0.3 to 1.5 carbon atoms per silicon atom.

14. (cancelled)

15. (previously presented) The laminate of claim 13 wherein said polysiloxane comprises (a) a polysilsesquioxane having repeating units of the formula



wherein R is a single group or mixture of substituted or unsubstituted alkyl or aryl groups having from one to seven carbon atoms; or

(b) condensates of hydrosylates of the formula $\text{R}_x\text{Si}(\text{OR}')_y$, wherein $x + y$ is 4 and x is from 0 to 2 and y is from 2 to 4; R is a single alkyl or aryl group or mixture of alkyl or aryl groups comprising up to 7 carbon atoms, optionally substituted with halogen atoms, mercapto groups, and/or epoxy groups; and R' is an alkyl radical with 1 to 4 carbon atoms.

16. (previously presented) The laminate of claim 13 wherein said overlay thermoset resin comprises at least one resin selected from the group consisting of phenolics, epoxies, polyesters, polyurethanes, and aminoplasts.

17. (original) The laminate of claim 13 wherein said decorative inner layer comprises a thermoset resin that is compatible with said overlay thermosettable resin.